



# MODERN MARBLE


Featuring warm and cool colors from Marble Onyx and Quartz, MODERN MARBLE creatively reproduces the elegant finishes in both polished and matte finishes.

FD02-01M


# MODERN MARBLE COLLECTION OPTIONS

---


## COLORS:



FD02-01M



FD02-02M



FD02-04M



FD02-05M



FD02-06M

## FINISH: MATTE or POLISHED

## SIZE:




12" x 24"




24" x 48"

## DECORS:



2" x 2" Mosaic  
on 12" x 12" sheet

## TRIMS:



6" x 12"  
Covebase



4" x 24"  
Bullnose




FD02-03M



# MODERN MARBLE

## PERFORMANCE DATA



Porcelain  
Stoneware



Floor



Wall



Moderate  
Variation




DCOF  
Compliant



Thickness  
8mm



Rectified  
Tile



No  
V.O.C.



Frost  
Proof



Low Water  
Absorption



USA  
Made/Stock

Technical Feature	Method	Value Required ANSI A 137.1	Studio Collection Results
Facial Dimension	ASTM C-499	$\pm 0.25\%$ or $\pm 0.03$ in	$\leq \pm 0.04$ in.
Wedging	ASTM C-502	$\pm 0.25\%$ or $\pm 0.03$ in	$\leq \pm 0.25\%$
Warpage Diagonal	ASTM C-485	$\pm 0.4\%$ or $0.07$ in	$\leq \pm 0.40\%$
Warpage Edge	ASTM C-485	$\pm 0.4\%$ or $0.05$ in	$\leq \pm 0.40\%$
Thickness	ASTM C-499	Range: $0.040$ inch max	$\leq \pm 0.25\%$
Water Absorption	ASTM C-373	$\leq 0.5\%$	$\leq 0.1\%$
Breaking Strength	ASTM C-648	$\geq 250$ lbs ( $\geq 1113$ N)	$\geq 400$ lbs.
Freeze Thaw	ASTM C-1026	No damages	No evidence of damage
Chemical Resistance	ASTM C-650	As reported	Class A
Dynamic Coefficient of Friction	ANSI A 326.3	$\geq 0.42$	$\geq 0.42$



# MODERN MARBLE —

