




## ONDA COLLECTION OPTIONS

## **COLORS:**




FINISH: MATTE

**SIZE:** 



**DECORS:** 



**TRIMS:** 







## ONDA PERFORMANCE DATA























Porcelain Stoneware

Floor

Wall

Slight Variation

DCOF Compliant

Thickness 9mm

Rectified Tile

No V.O.C.

Frost Low Water Proof Absorption

Water USA orption Made/Stock

Technical Feature	Method	Value Required ASNI A 137.1	Studio Collection Results
Facial Dimension	ASTM C-499	± 0.25% or ± 0.03 in	In accordance with ANSI A 137.1
Wedging	ASTM C-502	± 0.25% or ± 0.03 in	In accordance with ANSI A 137.1
Warpage diagonal	ASTM C-485	± 0.4% or 0.07 in	In accordance with ANSI A 137.1
Warpage edge	ASTM C-485	± 0.4% or 0.05 in	In accordance with ANSI A 137.1
Thickness	ASTM C-499	Range: 0.040 inch max	In accordance with ANSI A 137.1
Water absorption	ASTM C-373	≤ 0.5%	Passed "impervious tiles" Class P1
Breaking strength	ASTM C-648	≥ 250 lbs (≥ 1113N)	≥400 lbs
Freeze thaw	ASTM C-1026	No damages	No damages
Chemical Resistance	ASTM C-650	As reported	Unaffected
Dynamic Coefficient of Friction	ANSI A 326.3	≥ 0.42	≥ 0.42

## **ONDA**



